SONGHAN Plastic Technology Co., Ltd.

# 3M 8418 Polyester Film Tape

Category : Polymer , Adhesive

#### Material Notes:

Adhesive Type

3M<sup>™</sup> Polyester Film Tape 8417 is a self-wound (linerless) transparent polyester film coated with 3M<sup>™</sup> Adhesive 100 High-temperature Acrylic. It is often used as an overlaminate in conjunction with 3M<sup>™</sup> Polyester Film Tape 8418. 3M<sup>™</sup> Polyester Film Tape 8418 is a white polyester film coated with 3M Adhesive 100 High-temperature Acrylic and has a liner. Features:Adheres instantly to a variety of surfaces.Tough film backing resists edge tear when processing and dispensing.Non-corrosive and chemical resistant.High and low temperature stability.3M polyester film tape 8418 is printable with common processes and inks.3M polyester film tape 8417 provides good transparency when used as an overlaminate.When used together, the tapes pass all requirements for Federal Specification MIL-T-100B, Amendment 1 for non-corrosive, heat, cold and solvent-resistant identification tape. Applications:Fluid-line identification.General identification applications where chemical and temperature resistance is desired.Information provided by 3M

## Order this product through the following link:

### http://www.lookpolymers.com/polymer\_3M-8418-Polyester-Film-Tape.php

Physical Properties	Metric	English	Comments	
Thickness	25.4 microns	1.00 mil	Facestock	
	30.5 microns	1.20 mil	Adhesive	
	55.9 microns	2.20 mil	Total	

Mechanical Properties	Metric	English	Comments
Elongation at Break	100 %	100 %	
Peel Strength	0.1643 kN/m	0.9375 pli	Polypropylene, 180° Peel, 10 min dwell; ASTM D3330
	0.27391 kN/m	1.5625 pli	ABS, 180° Peel, 10 min dwell; ASTM D3330
	0.36156 kN/m	2.0625 pli	Stainless Steel, 180° Peel, 10 min dwell; ASTM D3330
	0.4163 kN/m	2.375 pli	Glass, 180° Peel, 10 min dwell; ASTM D3330
Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	
Descriptive Properties	Value		Comments

# Contact Songhan Plastic Technology Co.,Ltd.

100 High-temperature Acrylic)



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China