

## 3M 9626 Adhesive Transfer Tape with Quick Bonding Adhesive 360

Category : Polymer , Adhesive

**Material Notes:**

3M™ Adhesive Transfer Tapes with 3M™ Quick Bonding Adhesive 360 provides high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-9626-Adhesive-Transfer-Tape-with-Quick-Bonding-Adhesive-360.php](http://www.lookpolymers.com/polymer_3M-9626-Adhesive-Transfer-Tape-with-Quick-Bonding-Adhesive-360.php)

Physical Properties	Metric	English	Comments
Thickness	50.8 microns	2.00 mil	Adhesive
	81.3 microns	3.20 mil	Liner

Mechanical Properties	Metric	English	Comments
Peel Strength	0.60259 kN/m	3.4375 pli	LDPE, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	0.657 kN/m	3.75 pli	LDPE, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	0.71216 kN/m	4.0625 pli	HDPE, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	0.7669 kN/m	4.375 pli	HDPE, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.10 kN/m	6.25 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Faceside; ASTM D3330
	1.10 kN/m	6.25 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Backside; ASTM D3330
	1.10 kN/m	6.25 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Faceside; ASTM D3330
	1.10 kN/m	6.25 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Backside; ASTM D3330
	1.31 kN/m	7.50 pli	Polypropylene, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.424 kN/m	8.125 pli	Polypropylene, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.424 kN/m	8.125 pli	ABS, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.53 kN/m	8.75 pli	Stainless Steel, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.53 kN/m	8.75 pli	Polycarbonate, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
1.53 kN/m	8.75 pli	Polycarbonate, 180°, 2 mil al foil, 72	

Mechanical Properties	Metric	English	hr RT, Backside; ASTM D3330 Comments
	1.53 kN/m	8.75 pli	ABS, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.53 kN/m	8.75 pli	Stainless Steel, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	

Descriptive Properties	Value	Comments
Liner	Natural, 60#	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China