

3M Dyneon™ Fluorel™ FT-2350 Fluoroelastomer VF2 + HFP + TFE Terpolymer (discontinued **)

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Data provided by the manufacturer, Dyneon LLC. Incorporated cure polymer, 68.6%F in polymer with 22% Medium Thermal Carbon Black (N990), 2% MgO, and 4% Ca(OH)₂. Improved retention of elongation after long-term heat aging. Improved chemical and acid resistance over dipolymers. Used in Fabric Composite/Calendered Sheet Applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-Fluorel-FT-2350-Fluoroelastomer-VF2-HFP-TFE-Terpolymer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.86 g/cc	0.0672 lb/in ³	
Mooney Viscosity	56 @Temperature 121 °C	56 @Temperature 250 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	
Tensile Strength, Ultimate	15.0 MPa	2180 psi	
Tensile Strength, Yield	3.70 MPa	537 psi	M100
Elongation at Break	310 %	310 %	
Coefficient of Friction, Dynamic	0.80	0.80	
Compression Set	36 % @Temperature 200 °C	36 % @Temperature 392 °F	70 hr; ASTM D395B

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-14.0 °C	6.80 °F	TR10

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China