

3M Scotchkote™ GP 120 Epoxy Primer

Category : Polymer , Thermoset , Epoxy

Material Notes:

Scotchkote Epoxy Primer GP 120 has been specifically developed as an anti corrosive coating for steel structures that cannot be abrasive blast cleaned. Product Features: Suitable for use on mechanically prepared steelwork or high pressure water cleaned steel, can also be used on abrasive blasted steel. Can be applied over existing coatings. Can be used as a two coat primer/finish system or overcoated with a variety of top coats. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Scotchkote-GP-120-Epoxy-Primer.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	
Solids Content	90 %	90 %	
Volatile Organic Compounds (VOC) Content	83 g/l	83 g/l	
Thickness	3180 microns	125 mil	Dry
	3560 microns	140 mil	Wet

Processing Properties	Metric	English	Comments
Cure Time	360 min	6.00 hour	Touch Dry
	1440 min	24.0 hour	Hard Dry
	10100 min	168 hour	Full Cure

Descriptive Properties	Value	Comments
Appearance	Silver	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China