

## 3M Scotchkote™ XF 895 Fast Curing Floor Coating

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Liquid

**Material Notes:**

Scotchkote Fast Curing Floor Coating XF 895 has been specifically developed as a high build floor protection system for application to concrete surfaces, to provide rapid return to service. Product Features: Combines good application characteristics with excellent adhesion to concrete. Designed for application by brush or roller. Suitable for return to service in 1.5 hrs. Also suitable for use on asphalt floor surfaces in combination with 3M Scotchkote Primer FB 856. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Scotchkote-XF-895-Fast-Curing-Floor-Coating.php](http://www.lookpolymers.com/polymer_3M-Scotchkote-XF-895-Fast-Curing-Floor-Coating.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	
Solids Content	100 %	100 %	
Thickness	152 - 203 microns	6.00 - 8.00 mil	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75 - 80	75 - 80	ASTM D2240
Tensile Strength at Break	22.6 MPa	3280 psi	ASTM D638
Elongation at Break	15 - 20 %	15 - 20 %	ASTM D412
Abrasion	78	78	[mg] 1000 cycles

Processing Properties	Metric	English	Comments
Cure Time	45.0 - 60.0 min	0.750 - 1.00 hour	Touch Dry
	60.0 - 90.0 min	1.00 - 1.50 hour	Hard Dry
	10100 min	168 hour	Full Cure

Descriptive Properties	Value	Comments
Appearance	Light Gray, Clear	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China