

A. Schulman ComAlloy Comtuf® 152 Polypropylene, Mineral Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced, Impact Modified

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.20% Mineral Reinforced. Superior toughness and impact resistance characterize Comtuf® materialsThe ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-152-Polypropylene-Mineral-Reinforced-Impact-Modified.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Ultimate	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	180 %	180 %	ASTM D638
Flexural Strength	29.0 MPa	4210 psi	ASTM D790
Flexural Modulus	1.20 GPa	174 ksi	ASTM D790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	79.0 °C	174 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	64.0 °C	147 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China