

## A. Schulman ComAlloy Hiloy® 152 Polypropylene, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company.20% Mineral Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Hiloy-152-Polypropylene-Mineral-Reinforced.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-152-Polypropylene-Mineral-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ASTM D785
Tensile Strength, Ultimate	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	74.3 %	74.3 %	ASTM D638
Flexural Strength	49.0 MPa	7110 psi	ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	ASTM D790
Izod Impact, Notched	0.210 J/cm	0.393 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.60 J/cm	10.5 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 °C	244 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	69.0 °C	156 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	210 - 221 °C	410 - 430 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China