

A. Schulman ComAlloy Hiloy® 513 Polycarbonate, Glass Reinforced, UL

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.30% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-513-Polycarbonate-Glass-Reinforced-UL.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	117 MPa	17000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	190 MPa	27600 psi	ASTM D790
Flexural Modulus	7.90 GPa	1150 ksi	ASTM D790
Izod Impact, Notched	1.71 J/cm	3.20 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.01 J/cm	15.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	289 °F	ASTM D648
Glass Transition Temp, Tg	145 - 150 °C	293 - 302 °F	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	304 - 321 °C	579 - 610 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China