

A. Schulman ComAlloy Hiloy® 610 Nylon 6, Glass/Mineral Reinforced, UL

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass/Mineral Reinforced

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.45% Glass/Mineral Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-610-Nylon-6-GlassMineral-Reinforced-UL.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	145 MPa	21000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	203 MPa	29400 psi	ASTM D790
Flexural Modulus	10.8 GPa	1570 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.89 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	205 - 225 °C	401 - 437 °F	
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	260 - 271 °C	500 - 520 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China