

## A. Schulman ComAlloy Hiloy® 629 Nylon 6/6, Mineral Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

**Material Notes:**

Data provided by the manufacturer, ComAlloy International Company.40% Mineral Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Hiloy-629-Nylon-66-Mineral-Reinforced.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-629-Nylon-66-Mineral-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	90.0 MPa	13100 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	138 MPa	20000 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.35 J/cm	4.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	252 °C	486 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	175 °C	347 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	291 - 302 °C	556 - 576 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China