

A. Schulman ComAlloy Hiloy® 716 PPS, Carbon Fiber Reinforced

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.20% Carbon Fiber Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-716-PPS-Carbon-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	152 MPa	22000 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	216 MPa	31300 psi	ASTM D790
Flexural Modulus	15.9 GPa	2310 ksi	ASTM D790
Izod Impact, Notched	0.590 J/cm	1.11 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.95 J/cm	7.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	280 - 290 °C	536 - 554 °F	
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	229 °C	444 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	299 - 310 °C	570 - 590 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China