

A. Schulman ComAlloy Hiloy® 753 Glass Reinforced, Flow Enhanced, PPS Alloy, UL

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) Alloy, Glass Reinforced, Flow Enhanced

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.30% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-753-Glass-Reinforced-Flow-Enhanced-PPS-Alloy-UL.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Ultimate	124 MPa	18000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	203 MPa	29400 psi	ASTM D790
Flexural Modulus	9.30 GPa	1350 ksi	ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.80 J/cm	8.99 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	280 - 290 °C	536 - 554 °F	
Deflection Temperature at 0.46 MPa (66 psi)	271 °C	520 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	257 °C	495 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	299 - 310 °C	570 - 590 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China