

A. Schulman POLYFORT™ PP 2175HU Toyota High Flow Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Description Polyfort® PP 2175HU Toyota is a high flow copolymer polypropylene. Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-POLYFORT-PP-2175HU-Toyota-High-Flow-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.905 g/cc	0.905 g/cc	ASTM D792
Melt Flow	20 - 30 g/10 min @Temperature 230 °C	20 - 30 g/10 min @Temperature 446 °F	Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785
Tensile Strength, Yield	24.0 MPa	3480 psi	ASTM D638
Elongation at Break	>= 200 %	>= 200 %	ASTM D638
Flexural Modulus	1.135 GPa	164.6 ksi	ASTM D790
Izod Impact, Notched	0.750 J/cm	1.41 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	108 °C	226 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China