

A. Schulman POLYPUR™ CB 1110 Thermoplastic Polyurethane Compound

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded , Polyurethane, TP

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-POLYPUR-CB-1110-Thermoplastic-Polyurethane-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage	0.011 - 0.016 cm/cm	0.011 - 0.016 in/in	48 hr, at 121°C; ASTM D955
	@Thickness 3.20 mm	@Thickness 0.126 in	
	0.0090 - 0.014 cm/cm	0.0090 - 0.014 in/in	ASTM D955
	@Thickness 3.20 mm, Time 259000 sec	@Thickness 0.126 in, Time 72.0 hour	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	76	76	15 sec delay; ASTM D2240
Tensile Strength, Ultimate	37.0 MPa	5370 psi	2 in/min, at max load; ASTM D638
	44.0 MPa	6380 psi	20 in/min, at max load; ASTM D412
Elongation at Break	380 %	380 %	20 in/min; ASTM D412
Flexural Modulus	0.835 GPa	121 ksi	ASTM D790
Tear Strength	226 kN/m	1290 pli	2 in/min; ASTM D624

Thermal Properties	Metric	English	Comments
CTE, linear	150 µm/m-°C	83.3 µin/in-°F	ASTM E831
	@Temperature -30.0 - 30.0 °C	@Temperature -22.0 - 86.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China