

## A. Schulman POLYPUR™ FPU 1112 Thermoplastic Polyurethane Compound (15% Glass)

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Glass Fiber Reinforced

### Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-POLYPUR-FPU-1112-Thermoplastic-Polyurethane-Compound-15-Glass.php](http://www.lookpolymers.com/polymer_A-Schulman-POLYPUR-FPU-1112-Thermoplastic-Polyurethane-Compound-15-Glass.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Linear Mold Shrinkage	0.0090 - 0.014 cm/cm	0.0090 - 0.014 in/in	72 hr; ASTM D955
	@Thickness 3.20 mm	@Thickness 0.126 in	
	0.011 - 0.016 cm/cm	0.011 - 0.016 in/in	48 hr, at 121°C; ASTM D955
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	15 sec delay; ASTM D2240
Tensile Strength, Ultimate	38.0 MPa	5510 psi	at max load; ASTM D638
	40.0 MPa	5800 psi	
Elongation at Break	430 %	430 %	20 in/min; ASTM D412
Flexural Modulus	0.234 GPa	33.9 ksi	1.3 mm/min; ASTM D790
Tear Strength	207 kN/m	1180 pli	2 in/min; ASTM D624
Compression Set	24 %	24 %	Method B, 22 h, 70°C; ASTM D395
	25 %	25 %	

Thermal Properties	Metric	English	Comments
CTE, linear	120 µm/m-°C	66.7 µin/in-°F	ASTM E831
	@Temperature -30.0 - 30.0 °C	@Temperature -22.0 - 86.0 °F	

Descriptive Properties	Value	Comments
Heat Sag	8 mm	ASTM D3769, at 121°C, 6 in. over hang

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**