

A. Schulman PP 1329 Polypropylene Stabilized Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Description Polypropylene PP 1329 is a stabilized copolymer polypropylene. Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-PP-1329-Polypropylene-Stabilized-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D792
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.0 MPa	3770 psi	24 min.; ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Flexural Modulus	0.930 GPa	135 ksi	880 min.; ASTM D790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	40 min.; ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China