

## A. Schulman SCHULADUR® A GF50 50% Glass Fiber Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 50% Glass Fiber Filled

### Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-SCHULADUR-A-GF50-50-Glass-Fiber-Reinforced-PBT.php](http://www.lookpolymers.com/polymer_A-Schulman-SCHULADUR-A-GF50-50-Glass-Fiber-Reinforced-PBT.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.73 g/cc	1.73 g/cc	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm @Thickness 3.175 mm	0.0010 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	159 MPa	23000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	241 MPa	35000 psi	ASTM D790
Flexural Modulus	13.1 GPa	1900 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	9.61 J/cm	18.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	224 °C	435 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	216 °C	420 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 260 °C	482 - 500 °F	
Mold Temperature	30.0 - 65.6 °C	86.0 - 150 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**