

**A. Schulman SCHULADUR® B GF30 30% Glass Fiber Reinforced PET**

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

**Material Notes:**

Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-SCHULADUR-B-GF30-30-Glass-Fiber-Reinforced-PET.php](http://www.lookpolymers.com/polymer_A-Schulman-SCHULADUR-B-GF30-30-Glass-Fiber-Reinforced-PET.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	ASTM D792
Linear Mold Shrinkage	0.0019 cm/cm @Thickness 3.175 mm	0.0019 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ASTM D638
Elongation at Break	2.2 %	2.2 %	ASTM D638
Flexural Strength	221 MPa	32000 psi	ASTM D790
Flexural Modulus	9.65 GPa	1400 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm	1.70 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.41 J/cm	12.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	246 °C	475 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	226 °C	438 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 °C	536 - 572 °F	
Mold Temperature	90.0 - 110 °C	194 - 230 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**