

A. Schulman SCHULAMID® 66 GF20H 20% Glass Fiber Reinforced, Heat Stabilized Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-SCHULAMID-66-GF20H-20-Glass-Fiber-Reinforced-Heat-Stabilized-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	126 MPa	18300 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	6.55 GPa	950 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm	0.800 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.54 J/cm	8.50 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	243 °C	470 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	254 °C	490 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	290 - 310 °C	554 - 590 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	79.4 °C	175 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying
Moisture Content	0.080 - 0.12 %	0.080 - 0.12 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China