

ACC Magnifoam™ MF1-8055™ MTI Silicones Silicone Foam

Category : Polymer , Thermoset , Silicone , Silicone Foam

Material Notes:

Part of the Amber Chemical Group. Data provided by manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ACC-Magnifoam-MF1-8055-MTI-Silicones-Silicone-Foam.php

Physical Properties	Metric	English	Comments
Density	0.128 g/cc	0.00463 lb/in ³	ASTM D1056

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	0.103 MPa	15.0 psi	ASTM D412
Elongation at Break	100 %	100 %	ASTM D412
Compression Set	0.00 %	0.00 %	at 50%, 22 hrs @ 70°C; ASTM D1056
	0.00 %	0.00 %	at 50%, 22 hrs; ASTM D1056
	@Temperature 100 °C	@Temperature 212 °F	

Thermal Properties	Metric	English	Comments
Flammability Test	<= 25	<= 25	ASTM E162/D 3675
Smoke Density	1.5 min	1.5 min	<20; ASTM E662
	4.0 min	4.0 min	<50; ASTM E662

Descriptive Properties	Value	Comments
Durability	0% Height Loss	Jounce & Squirm (1,000,000 cycles)
IFD, lbs	55	ASTM S3574 B1 @ 2" thick
Noise Reduction-Coefficient	0.65	ASTM C423-90a
Thermal Resistance, ft2-h/BTU	2.7	ASTM C518
Toxic Gas Emission	Pass	Bombardier SMP 800C
Vertical Flammability	Pass	FAR25.83(a)(1)(i) 12sec
	Pass	FAR25.83(a)(1)(i) 60sec

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China