

AK Steel PH 15-7 Mo® Precipitation Hardening Stainless Steel, Condition A

Category : Metal , Ferrous Metal , Austenitic , Stainless Steel , Precipitation Hardening Stainless

Material Notes:

AK Steel 15-7 Mo® provides high strength and hardness, good corrosion resistance and minimum distortion on heat treatment. It is easily formed in the annealed condition and develops effective balance of properties by simple heat treatment. This alloy is useful for a wide range of applications that include retaining rings, springs, diaphragms, aircraft bulkheads, welded and brazed honeycomb paneling and other aircraft components requiring high strength at elevated temperatures. The material supplied from the mill is in Condition A. After fabrication, and conditioning treatments, the material is precipitation hardened into either Condition TH 1050 or Condition RH 950. To achieve the highest mechanical properties Condition A material is transformed to martensite at the mill by cold reduction to Condition C. After fabrication by the user a single low-temperature heat treatment is performed to achieve condition CH 900. Information provided by AK Steel

Order this product through the following link:

http://www.lookpolymers.com/polymer_AK-Steel-PH-15-7-Mo-Precipitation-Hardening-Stainless-Steel-Condition-A.php

Physical Properties	Metric	English	Comments
Density	7.804 g/cc	0.2819 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	88	88	
Tensile Strength, Ultimate	896 MPa	130000 psi	
Tensile Strength, Yield	372 MPa @Strain 0.200 %	54000 psi @Strain 0.200 %	
Elongation at Break	35 %	35 %	in 2 inches
Modulus of Elasticity	200 GPa	29000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	14.4 µm/m-°C @Temperature 21.0 - 93.0 °C	8.00 µin/in-°F @Temperature 69.8 - 199 °F	
	16.9 µm/m-°C @Temperature <=538 °C	9.39 µin/in-°F @Temperature <=1000 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.75 - 1.5 %	0.75 - 1.5 %	

Carbon, C Component Elements Properties	$\leq 0.090\%$ Metric	$\leq 0.090\%$ English	Comments
Chromium, Cr	14 - 16 %	14 - 16 %	
Iron, Fe	69.58 - 76.75 %	69.58 - 76.75 %	As Remainder
Manganese, Mn	$\leq 1.0\%$	$\leq 1.0\%$	
Molybdenum, Mo	2.0 - 3.0 %	2.0 - 3.0 %	
Nickel, Ni	6.5 - 7.75 %	6.5 - 7.75 %	
Phosphorous, P	$\leq 0.040\%$	$\leq 0.040\%$	
Silicon, Si	$\leq 1.0\%$	$\leq 1.0\%$	
Sulfur, S	$\leq 0.040\%$	$\leq 0.040\%$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China