

## ATG s.r.l. SBR Styrene-Butadiene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ATG-srl-SBR-Styrene-Butadiene-Rubber.php](http://www.lookpolymers.com/polymer_ATG-srl-SBR-Styrene-Butadiene-Rubber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	35 - 95	35 - 95	
Tensile Strength, Ultimate	7.00 - 28.0 MPa	1020 - 4060 psi	
Elongation at Break	125 - 850 %	125 - 850 %	
Rebound	25 - 55 %	25 - 55 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Abrasion Resistance	high	
Chemical Resistance to Animal and Vegetable Oils and Greases	low	
Chemical Resistance to Aromatic Hydrocarbons	none	
Chemical Resistance to Chloride Solvents	none	
Chemical Resistance to Distilled Water	medium	
Chemical Resistance to Ketones	medium	
Chemical Resistance to Maximum Concentrated Alkalis (at 50°C)	medium	
Chemical Resistance to Medium-High Concentrated Acids (at 50°C)	low	
Chemical Resistance to Mineral Oils and Aliphatic Hydrocarbons	none	
Compression set at 100°C	medium	
Impermeability at gas (Oxygen and Nitrogen)	low	

<b>Resistance to Flame Descriptive Properties</b>	<b>Value</b>	<b>Comments</b>
Resistance to Heat Aging	low	
Resistance to Low Temperatures	medium	
Resistance to Ozone and Weathering	low	
Tear Strength	medium	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China