

## Abatron AboWeld 8012-6/AboCure 8012-6 Epoxy (discontinued \*\*)

Category : Polymer , Thermoset , Epoxy

### Material Notes:

Data provided by the manufacturer, Abatron, Inc. Iron filled putty, "plastic steel". non-shrinking, adhesive filler. Shelf life is 12+ months. Processing: Pot life: 1-2 hrs. 2/1 ratio. Applications: All-purpose structural adhesive, high-strength filler and metal patching compound.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboWeld-8012-6AboCure-8012-6-Epoxy-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Abatron-AboWeld-8012-6AboCure-8012-6-Epoxy-nbspdiscontinued-.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	Typical value for Abatron "VR" Epoxies.
Tensile Strength, Ultimate	55.0 MPa	7980 psi	Typical value for Abatron "VR" Epoxies.
Compressive Yield Strength	62.0 MPa	8990 psi	Typical value for Abatron "VR" Epoxies.

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 - 110 °C	212 - 230 °F	Heat distortion temperature

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China