

## Aclo Accucomp Polypropylene CPO407L Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accucomp-Polypropylene-CPO407L-Copolymer.php](http://www.lookpolymers.com/polymer_Aclo-Accucomp-Polypropylene-CPO407L-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	MD; ASTM D955
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	60	60	ASTM D785
Tensile Strength at Break	13.0 MPa	1890 psi	ASTM D638
Tensile Strength, Yield	18.0 MPa	2610 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Tensile Modulus	0.800 GPa	116 ksi	ASTM D638
Flexural Strength	21.0 MPa	3050 psi	ASTM D790
Flexural Modulus	0.800 GPa	116 ksi	ASTM D790
Izod Impact, Notched	6.73 J/cm	12.6 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	62.8 °C	145 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	43.9 °C	111 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China