

Aclo Accutech Polyethylene HD0234G30UVL High Density Glass Reinforced UV Stabilized

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Glass fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polyethylene-HD0234G30UVL-High-Density-Glass-Reinforced-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	MD; ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	52	52	ASTM D785
Tensile Strength at Break	45.0 MPa	6530 psi	ASTM D638
Tensile Strength, Yield	45.0 MPa	6530 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	3.699 GPa	536.5 ksi	ASTM D638
Flexural Strength	57.0 MPa	8270 psi	ASTM D790
Flexural Modulus	3.699 GPa	536.5 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	129 °C	264 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China