

## Aclo Accutech Polypropylene Homopolymer HP0336G15M15CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G15M15CL-GlassMineral-Reinforced-Coupled.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G15M15CL-GlassMineral-Reinforced-Coupled.php)

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	MD; ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	87	87	ASTM D785
Tensile Strength at Break	49.0 MPa	7110 psi	ASTM D638
Tensile Strength, Yield	51.0 MPa	7400 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.699 GPa	536.5 ksi	ASTM D638
Flexural Strength	80.0 MPa	11600 psi	ASTM D790
Flexural Modulus	4.599 GPa	667.1 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	152 °C	306 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	118 °C	244 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**