

Aclo Accutech Polypropylene Homopolymer HP0336M40L Mica Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Mica Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336M40L-Mica-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	MD; ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	55	55	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Tensile Strength, Yield	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	4.300 GPa	623.6 ksi	ASTM D638
Flexural Strength	44.0 MPa	6380 psi	ASTM D790
Flexural Modulus	4.599 GPa	667.1 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.750 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	123 °C	253 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	81.1 °C	178 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China