

Aclo Accutech Polypropylene Homopolymer HP0336T40L1 Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336T40L1-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	80	80	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Tensile Strength, Yield	33.0 MPa	4790 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.20 GPa	319 ksi	ASTM D638
Flexural Strength	49.0 MPa	7110 psi	ASTM D790
Flexural Modulus	4.000 GPa	580.1 ksi	ASTM D790
Izod Impact, Notched	0.299 J/cm	0.560 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	135 °C	275 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.2 °C	180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China