

Aearo E-A-R Specialty Composites Isoloss® HD Polyurethane Elastomer

Category: Polymer, Thermoset, Polyurethane, TS, Thermoset Polyurethane, Elastomer, Unreinforced, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Isoloss® Polyurethane Elastomers feature high internal damping properties for low amplification at resonance to protect equipment during frequency cycling and random shocks, effective shock protection for sensitive mechanisms within minimum sway parameters, and quick return to equilibrium after vibrations or shocks.Information provided by Aearo E-A-R Specialty Composites.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aearo-E-A-R-Specialty-Composites-Isoloss-HD-Polyurethane-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	56	56	
Tensile Strength at Break	9.79 MPa	1420 psi	
Elongation at Break	424 %	424 %	
Resilience	4.5	4.5	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.0 °C	180 °F	
Brittleness Temperature	-27.0 °C	-16.6 °F	
Flammability, UL94	НВ	НВ	Meets HBF

Descriptive Properties	Value	Comments
Abrasion Resistance	Excellent	
Compression Set Resistance	Excellent	
Damping T max	4 dB	
Heat Aging; 100°C	Fair to Good	
Tear Strength	Excellent	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China