

Akro-Plastic Akromid® A3 GF 25 (2420) PA 6.6 Conditioned, 25% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

AKROMID® A (Polyamide 6.6) is an engineering compound, characterized by high mechanical strength, stiffness and thermal resistance. Furthermore, this polyamide offers high toughness at low temperatures as well as easy processing. AKROMID® A is an engineering plastic compound that allows a broad range of possible applications. On the basis of these standard types, we are able to develop individual compounds for special application needs. Information from Akro-Plastic

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akro-Plastic-Akromid-A3-GF-25-2420-PA-66-Conditioned-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	ISO 1183
Filler Content	25 %	25 %	ISO 1172
Water Absorption	2.0 - 2.2 % @Temperature 70.0 °C	2.0 - 2.2 % @Temperature 158 °F	62% r.h., Humidity; ISO 62
Water Absorption at Saturation	5.7 - 6.3 % @Time 82800 sec	5.7 - 6.3 % @Time 23.0 hour	ISO 62
Linear Mold Shrinkage, Flow	0.0024 cm/cm	0.0024 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.013 cm/cm	0.013 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	5 [mm/min]; ISO 527-1/2
Elongation at Break	6.5 %	6.5 %	5 [mm/min]; ISO 527-1/2
Tensile Modulus	6.00 GPa	870 ksi	1[mm/min]; ISO 527-1/2
Flexural Strength	200 MPa	29000 psi	2 [mm/min]; ISO 178
Flexural Modulus	6.20 GPa	899 ksi	2 [mm/min]; ISO 178
Charpy Impact Unnotched	9.00 J/cm ² @Temperature 23.0 °C	42.8 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	1.30 J/cm ² @Temperature 23.0 °C	6.19 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	ISO 11357-1/3

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China