

## Akro-Plastic Akromid® T1 GF 30 9 (3498) PPA Dry, 30% Glass Filled

Category : Polymer , Thermoplastic , Polyphthalamide (PPA) , Polyphthalamide (PPA), 30% Glass Fiber Reinforced

### Material Notes:

The new AKROMID® T is characterized primarily by high heat resistance and the lowest moisture absorption of the three PA grades, making it particularly well-suited in the automotive sector for high-temperature applications in the engine compartment and in machine building for components subjected to high mechanical loads. It easily maintains its high initial stability even at temperatures of up to 140 °C and still exhibits phenomenal creep behaviour. This extremely high dimensional stability is further enhanced by the product's low moisture absorption. Another key advantage over PA 6 or PA 6.6 is the significantly improved chemical resistance and high resistance to hydrolytic degradation. These properties – along with the aforementioned advantages in terms of mechanical loading – make the material an ideal answer for difficult applications in industrial pumps and fluid filters. Its low water absorption over extended periods is yet another advantage. By modifying the base grades, we have also made the material suitable for applications requiring a high quality surface finish.

**Applications:**

**Automotive Sector:** Cooling system (thermostat housing, connectors, etc.) Parts in the oil circuit (tensioner bases, etc.) Parts in the brake system (valve bodies, etc.) Clutch components (central clutch release bearing, etc.) Air ducting parts (side pieces for charge-air coolers, control shafts, etc.) Parts subjected to high loads in the interior (centre armrest, etc.)

**Electrical Engineering:** Mobile telephone parts (chip carrier, etc.) Coil formers Motor parts (brush holders, etc.) Plugs and connectors Bulb and LED sockets

**Industry and Household:** Heating systems (fan housings, etc.) Components for coffee machines (grades compliant with KTW- German recommendation for polymers in drinking-water systems) Water counters and water filters (KTW-compliant, hot water) Pump systems (misc. functional parts)

Information from Akro-Plastic

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Akro-Plastic-Akromid-T1-GF-30-9-3498-PPA-Dry-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Akro-Plastic-Akromid-T1-GF-30-9-3498-PPA-Dry-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in <sup>3</sup>	ISO 1183
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Filler Content	30 %	30 %	ISO 1172
Water Absorption	1.3 %	1.3 %	50% r.h.; ISO 62
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	270 MPa	39200 psi	HB 961/30; ISO 2039-1
Tensile Strength at Break	210 MPa	30500 psi	5 [mm/min]; ISO 527-1/2
	105 MPa	15200 psi	5 [mm/min], 50% Loss of Tensile Strength; ICE 216
	@Temperature 150 - 160 °C, Time 1.80e+7 sec	@Temperature 302 - 320 °F, Time 5000 hour	
	105 MPa	15200 psi	5 [mm/min], 50% Loss of Tensile

Mechanical Properties	@Temperature 130 - 140 °C, Metric	@Temperature 266 - 280 °F, English	Strength: ICE 216 Comments
	Time 7.20e+7 sec	Time 20000 hour	
Elongation at Break	2.4 %	2.4 %	5 [mm/min]; ISO 527-1/2
	3.0 %	3.0 %	2 [mm/min], Flexural; ISO 178
Tensile Modulus	12.0 GPa	1740 ksi	1[mm/min]; ISO 527-1/2
Flexural Strength	300 MPa	43500 psi	2 [mm/min]; ISO 178
Flexural Modulus	11.0 GPa	1600 ksi	2 [mm/min]; ISO 178
Charpy Impact Unnotched	4.50 J/cm <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	308 °C	586 °F	ISO 11357-1, DSC,10 [K/min]
Deflection Temperature at 1.8 MPa (264 psi)	275 °C	527 °F	HDT/A; ISO 75-1/2
Deflection Temperature at 8.0 MPa	165 °C	329 °F	HDT/C; ISO 75-2
Flammability, UL94	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	Test Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Feed Temperature	80.0 - 95.0 °C	176 - 203 °F	
Nozzle Temperature	320 - 330 °C	608 - 626 °F	
Zone 1	310 - 320 °C	590 - 608 °F	
Zone 2	315 - 325 °C	599 - 617 °F	
Zone 3	320 - 335 °C	608 - 635 °F	
Zone 4	320 - 335 °C	608 - 635 °F	
Melt Temperature	325 - 340 °C	617 - 644 °F	

Mold Temperature Processing Properties	100 - 130 °C Metric	212 - 266 °F English	Comments
Drying Temperature	90.0 °C	194 °F	
Dry Time	2 - 16.0 hour	2 - 16.0 hour	
Hold Pressure	30.0 - 80.0 MPa	4350 - 11600 psi	
Back Pressure	0.200 - 0.650 MPa	29.0 - 94.3 psi	

Descriptive Properties	Value	Comments
Acetic acid	Fail	100% Conc
Acetone	Pass	100% Conc
Cresol	Fail	100% Conc
Diesel fuel (DIN 51601)	Pass	100% Conc
Drying, Moisture (%)	<0.1	
Engine oil	Pass	100% Conc
Ethanol	Pass	96% Conc
Ethylene glycol/water	Pass	120°C, 50% Conc
Formic acid	Fail	100% Conc
Hydraulic oil	Pass	100% Conc
Injection Speed	average to high	
Isopropanol	Pass	100% Conc
Kerosene	Pass	100% Conc
Methanol	Pass	100% Conc
Petrol	Pass	100% Conc
Phenol	Fail	100% Conc
Rate acc. FMVSS 302 (	Passed	
Rate acc. FMVSS 302,(	FMVSS 302, >1 [mm] Thickness	
Silicone oil	Pass	
Sulphuric acid	Fail	96% Conc
Toluene	Pass	100% Conc

Urea, aqueous Descriptive Properties	Pass Value	20% Conc Comments
Water	Pass	100% Conc
Xylene	Pass	100% Conc
Zinc chloride, aqueous	Pass	50% Conc

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China