

## Alliance A-6S Alnico Magnetic Material

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Cobalt Alloy , Nickel Alloy

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-A-6S-Alnico-Magnetic-Material.php](http://www.lookpolymers.com/polymer_Alliance-A-6S-Alnico-Magnetic-Material.php)

Physical Properties	Metric	English	Comments
Density	6.90 - 7.30 g/cc	0.249 - 0.264 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	300 - 500	300 - 500	
Tensile Strength, Ultimate	80.0 - 300 MPa	11600 - 43500 psi	
Modulus of Elasticity	100 - 200 GPa	14500 - 29000 ksi	
Compressive Strength	300 - 400 MPa	43500 - 58000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	10.0 - 13.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	5.56 - 7.22 $\mu\text{in}/\text{in}\cdot\text{°F}$	Parallel DOM
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Specific Heat Capacity	0.350 - 0.500 J/g·°C	0.0837 - 0.120 BTU/lb·°F	
Thermal Conductivity	10.0 - 200 W/m·K	69.4 - 1390 BTU-in/hr-ft <sup>2</sup> ·°F	
Maximum Service Temperature, Air	450 °C	842 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000400 - 0.0000700 ohm-cm	0.0000400 - 0.0000700 ohm-cm	
Magnetic Coercive Force, Hc	700 Oe	700 Oe	
	710 Oe	710 Oe	Intrinsic
Magnetic Remanence, Br	10000 Gauss	10000 Gauss	
Magnetic Maximum Energy Product, BH	3.0 MGOe	3.0 MGOe	
Curie Temperature	850 °C	1560 °F	

Descriptive Properties	Value	Comments
Reversible Temp Coef., Bd	-0.02 %/°C	
Temperature Coefficient, Br	-0.025 %/°C	(20-100°C)
Temperature Coefficient, Hci	+0.01 %/°C	(20-100°C)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China