

AlphaGary Garaflex™ O 9777-A2 Olefinic Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO) , Polyolefin , Polyolefin, Wire/Cable Grade

Material Notes:

Garaflex™ O is a flame retarded, olefinic thermoplastic elastomer 105°C Rated TPE for Lightweight Pump Cable

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-Garaflex-O-9777-A2-Olefinic-Thermoplastic-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80 - 85	80 - 85	
Tensile Strength	13.8 MPa	2000 psi	
Elongation at Break	600 %	600 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China