

## Ametek 17-4 P/M Process, Sintered at 2050°F (1121°C)

Category : Metal , Ferrous Metal , Stainless Steel , Precipitation Hardening Stainless

### Material Notes:

Composition reported is typical of 17-4 precipitation hardening stainless. This alloy is widely used because of its high strength, high hardness, excellent corrosion resistance, and easy heat treatment. The 17-4 PH alloy is used in aerospace, medical, food processing, and chemical industries for applications such as pump shafts, valve stems, braces, fasteners, coupling, rocket and missile components, hydraulic actuators, and wear rings. Mechanical property data below is from samples aged for 1 hour at 900°F (482°C) in hydrogen - the H900 condition, which maximizes strength. The properties that can be expected for material that was lubricated with 3/4% Acrawax C and compacted at 48 tsi are shown below. 17-4 PH is a registered trademark of Armco, Inc.; information provided by Ametek Specialty Metal Product Division.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ametek-17-4-PM-Process-Sintered-at-2050F-1121C.php](http://www.lookpolymers.com/polymer_Ametek-17-4-PM-Process-Sintered-at-2050F-1121C.php)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	80	80	
Tensile Strength, Ultimate	310 MPa	45000 psi	
Tensile Strength, Yield	290 MPa	42100 psi	
Elongation at Break	0.30 %	0.30 %	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.035 %	0.035 %	
Chromium, Cr	16.3 %	16.3 %	
Copper, Cu	4.0 %	4.0 %	
Iron, Fe	74 %	74 %	as balance
Manganese, Mn	0.50 %	0.50 %	
Nickel, Ni	4.0 %	4.0 %	
Niobium, Nb (Columbium, Cb)	0.30 %	0.30 %	
Phosphorous, P	0.020 %	0.020 %	
Silicon, Si	0.50 %	0.50 %	
Sulfur, S	0.015 %	0.015 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China