

Ametek AM 388™ Alloy (UNS C72650) TM06

Category: Metal, Nonferrous Metal, Copper Alloy

Material Notes:

Information supplied by Ametek Specialty Metal Products Division. Copper base Spinodal alloy with high conductivity and high strength.

Outstanding performance for contacts in connectors, sockets and switches. Benefits include combination of high strength and formability, high conductivity, available in mill hardened or age hardenable tempers, no distortion during aging, no fixturing required, excellent solderability and resistance to stress relaxation during high temperature (over 400°F, 200°C) soldering, fine grain size, excellent corrosion resistance bare and easy to plate when required, low initial cost, and additional savings during processing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-AM-388-Alloy-UNS-C72650-TM06.php

Physical Properties	Metric	English	Comments
Density	8.87 g/cc	0.320 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	300 - 360	300 - 360	
Tensile Strength, Ultimate	827 - 965 MPa	120000 - 140000 psi	
Tensile Strength, Yield	723 - 861 MPa	105000 - 125000 psi	
Elongation at Break	10 - 14 %	10 - 14 %	
Modulus of Elasticity	124 GPa	18000 ksi	

Component Elements Properties	Metric	English	Comments
Copper, Cu	87 %	87 %	as balance
Nickel, Ni	7.0 - 8.0 %	7.0 - 8.0 %	
Other	<= 0.50 %	<= 0.50 %	
Tin, Sn	4.5 - 5.5 %	4.5 - 5.5 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000115 - 0.0000123 ohm-cm	0.0000115 - 0.0000123 ohm-cm	Conductivity 14 - 15% IACS

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China