

Ametek AM 388™ Alloy (UNS C72650) TS04

Category: Metal, Nonferrous Metal, Copper Alloy

Material Notes:

Information supplied by Ametek Specialty Metal Products Division. Copper base Spinodal alloy with high conductivity and high strength. Outstanding performance for contacts in connectors, sockets and switches. Benefits include combination of high strength and formability, high conductivity, available in mill hardened or age hardenable tempers, no distortion during aging, no fixturing required, excellent solderability and resistance to stress relaxation during high temperature (over 400°F, 200°C) soldering, fine grain size, excellent corrosion resistance bare and easy to plate when required, low initial cost, and additional savings during processing. Spinodal Age Hardening Treatment 725°F (385°C)/2 hrs.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-AM-388-Alloy-UNS-C72650-TS04.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------------------|----------|
| Density | 8.87 g/cc | 0.320 lb/in ³ | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-----------------|---------------------|----------|
| Hardness, Vickers | 320 - 380 | 320 - 380 | |
| Tensile Strength, Ultimate | 965 - 1068 MPa | 140000 - 154900 psi | |
| Tensile Strength, Yield | 896 - 999 MPa | 130000 - 145000 psi | |
| | @Strain 0.200 % | @Strain 0.200 % | |
| Elongation at Break | 4.0 - 6.0 % | 4.0 - 6.0 % | typical |
| Modulus of Elasticity | 124 GPa | 18000 ksi | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|-------------|-------------|------------|
| Copper, Cu | 87 % | 87 % | as balance |
| Nickel, Ni | 7.0 - 8.0 % | 7.0 - 8.0 % | |
| Other | <= 0.50 % | <= 0.50 % | |
| Tin, Sn | 4.5 - 5.5 % | 4.5 - 5.5 % | |

| Electrical Properties | Metric | English | Comments |
|------------------------|---------------------------------|---------------------------------|----------------------------|
| Electrical Resistivity | 0.0000115 - 0.0000123 ohm-cm | 0.0000115 - 0.0000123 ohm-cm | Conductivity 14 - 15% IACS |

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China