

Ametek High Purity Nickel Strip 899L Skin Hard

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Information supplied by Ametek Specialty Metal Products. AMETEK High Purity Nickel offers major advantages to the rechargeable battery industry, including: Lowest electrical resistivity available in pure nickel strip. Homogeneity, microcleanliness, and close composition control enhances weldability. Significantly low levels of surface oxides reduces die wear and provides excellent solderability. Excellent formability. Typical applications for rechargeable batteries: computers, cellular phones, power tools, electric vehicles, pagers, and camcorders.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-High-Purity-Nickel-Strip-899L-Skin-Hard.php

Physical Properties	Metric	English	Comments
Density	8.90 g/cc	0.322 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	64 - 70	64 - 70	
Hardness, Vickers	110 - 126	110 - 126	
Tensile Strength, Ultimate	359 - 448 MPa	52100 - 65000 psi	
Tensile Strength, Yield	138 - 310 MPa @Strain 0.200 %	20000 - 45000 psi @Strain 0.200 %	
Elongation at Break	30 - 40 %	30 - 40 %	typical
Poissons Ratio	0.31	0.31	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	86.0 W/m-K @Temperature 70.0 °C	597 BTU-in/hr-ft ² -°F @Temperature 158 °F	
Melting Point	1453 °C	2647 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.0050 - 0.020 %	0.0050 - 0.020 %	
Copper, Cu	<= 0.0050 %	<= 0.0050 %	
Iron, Fe	<= 0.050 %	<= 0.050 %	
Manganese, Mn	<= 0.070 %	<= 0.070 %	

Nickel Ni Component Elements Properties	99.8 % Metric	99.8 % English	Comments
Silicon, Si	<= 0.0010 %	<= 0.0010 %	
Sulfur, S	<= 0.0010 %	<= 0.0010 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000763 ohm-cm @Temperature 20.0 °C	0.00000763 ohm-cm @Temperature 68.0 °F	
Curie Temperature	353 °C	667 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China