

Ametek P303L P/M Stainless Steel, Sintered from 6.5 g/cc Green Density

Category : Metal , Ferrous Metal , Stainless Steel , T 300 Series Stainless Steel

Material Notes:

Powder apparent bulk density 2.8 g/cc; powder flow 30 sec/50g. Compacting properties measured on powders with 1% lithium stearate. Sintering was done in dissociated ammonia at 1121°C (2050°F) for 45 minutes. Sintered properties below were determined using transverse rupture bars. Compacting pressure 40 tsi. Green strength 900 psi. Sintered breaking strength 91 ksi. Dimensional change from die size - 0.44%. Information provided by Ametek Specialty Metal Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-P303L-PM-Stainless-Steel-Sintered-from-65-gcc-Green-Density.php

Physical Properties	Metric	English	Comments
Density	6.60 g/cc	0.238 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	50	50	
Tensile Strength, Ultimate	350 MPa	50800 psi	
Elongation at Break	4.8 %	4.8 %	

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.030 %	<= 0.030 %	
Chromium, Cr	17 - 19 %	17 - 19 %	
Iron, Fe	65 - 75 %	65 - 75 %	as balance
Manganese, Mn	<= 2.0 %	<= 2.0 %	
Nickel, Ni	8.0 - 13 %	8.0 - 13 %	
Phosphorous, P	<= 0.045 %	<= 0.045 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	0.15 - 0.30 %	0.15 - 0.30 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China