

Amity Thermosets ATS 1612 Phenolic Molding Nylon, inorganic, and glass Filler, Compression Molded

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic

Material Notes:

Characteristics:High dielectric & mechanical strengthWeather resistant Good electric insulationLow water absorption Good mechanical tension bearing capacityColor-blackSoft/Medium flow Applications:Railway signaling equipment parts Kitchen equipment (e.g. mixers, dishwashers) parts Components which ought to have good electric insulation in spite of exposure to humid atmosphere, etc.Information provided by Amity Thermosets Limited

Order this product through the following link:

http://www.lookpolymers.com/polymer_Amity-Thermosets-ATS-1612-Phenolic-Molding-Nylon-inorganic-and-glass-Filler-Compression-Molded.php

Physical Properties	Metric	English	Comments
Density	1.45 - 1.55 g/cc	0.0524 - 0.0560 lb/in ³	Molding; IS 867-1963
Apparent Bulk Density	0.700 - 0.750 g/cc	0.0253 - 0.0271 lb/in ³	IS 867-1963
Water Absorption	0.12 - 0.18 %	0.12 - 0.18 %	IS 13411-1993
Linear Mold Shrinkage	0.0035 - 0.0055 cm/cm	0.0035 - 0.0055 in/in	IS 13411-1992

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 - 65.0 MPa	7980 - 9430 psi	5 mm/min.; IS 867-1963
Shear Strength	77.0 - 88.0 MPa	11200 - 12800 psi	2mm/min.; IS 867-1963
Izod Impact, Notched	0.250 - 0.400 J/cm	0.468 - 0.749 ft-lb/in	IS 13411-1992

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.2e+11 - 1.0e+12 ohm-cm	3.2e+11 - 1.0e+12 ohm-cm	IS 3396-1979
Surface Resistance	1.00e+11 - 3.16e+11 ohm	1.00e+11 - 3.16e+11 ohm	IS 3396-1979
Dielectric Strength	7.00 - 9.00 kV/mm @Temperature 90.0 °C	178 - 229 kV/in @Temperature 194 °F	IS 2584-1963

Processing Properties	Metric	English	Comments
Mold Temperature	160 - 180 °C	320 - 356 °F	
Injection Pressure	15.68 - 34.3 MPa	2274 - 4970 psi	Mold Pressure
Cure Time	0.833 - 1.33 min	0.0139 - 0.0222 hour	per mm

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China