

## ArcelorMittal 16 High formability steel for drawing, Hot rolled

Category : Metal , Ferrous Metal , Alloy Steel

**Material Notes:**

Description: This range of non-alloyed mild steels is designed for deep and extra deep drawing applications. These products are used extensively in the automotive industry, both for visible and structural parts. The guaranteed low scatter in their mechanical properties ensures optimum productivity in drawing press operations. The range of cold rolled steels has been extended to include the ultra high drawability quality. ArcelorMittal 07, ensuring maximum efficiency in the production of the most difficult- to-form parts (body sides, door liners, tailgates, etc.). The range of ArcelorMittal hot rolled mild steels covers the four levels of drawing difficulty listed below: ArcelorMittal 12: for drawing, with minimum guaranteed yield strength ArcelorMittal 13: for deep drawing ArcelorMittal 14: for very deep drawing ArcelorMittal 15: for drawing particularly difficult parts requiring performance regularity at high production rates (transfer presses). These ArcelorMittal steel grades are non-ageing, conserving their mechanical properties and their formability over time. They are also suitable for class 1 hot dip galvanizing according to the EN 36503 standard. The ArcelorMittal range offers better guarantees than the usual standard-compliant drawing steels, while remaining compatible with standards. Applications: These ArcelorMittal steels are designed for deep and extra deep drawing of visible and structural parts. Information provided by ArcelorMittal

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ArcelorMittal-16-High-formability-steel-for-drawing-Hot-rolled.php](http://www.lookpolymers.com/polymer_ArcelorMittal-16-High-formability-steel-for-drawing-Hot-rolled.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	270 - 350 MPa	39200 - 50800 psi	
Tensile Strength, Yield	180 - 260 MPa	26100 - 37700 psi	
Elongation at Break	>= 33 %	>= 33 %	L<Sub>0</sub>=80 mm, th<3 mm
	>= 40 %	>= 40 %	L<Sub>0</sub>=5.65v <Sub>0</sub> mm, th<3 mm

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.080 %	<= 0.080 %	
Iron, Fe	>= 99.59 %	>= 99.59 %	as balance
Manganese, Mn	<= 0.30 %	<= 0.30 %	
Silicon, Si	<= 0.030 %	<= 0.030 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China