

## Aremco Aremco-Seal™ 529VHV High Temperature Specialty Coatings Silicone

Category : Polymer , Adhesive , Thermoset , Silicone

### Material Notes:

Very high viscosity version, transparent silicone sealer with exceptional electrical and moisture resistance to 600°F (316°C). Ideal for use in cartridge heaters.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aremco-Aremco-Seal-529VHV-High-Temperature-Specialty-Coatings-Silicone.php](http://www.lookpolymers.com/polymer_Aremco-Aremco-Seal-529VHV-High-Temperature-Specialty-Coatings-Silicone.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	
Solids Content	75.3 %	75.3 %	by volume
	80 %	80 %	by weight
Volatile Organic Compounds (VOC) Content	273 g/l	273 g/l	
Viscosity	12000 - 14000 cP	12000 - 14000 cP	
Thickness	25.4 microns	1.00 mil	recommended dry film thickness
	33.8 microns	1.33 mil	estimated wet film thickness
Storage Temperature	4.44 - 32.2 °C	40.0 - 90.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	316 °C	600 °F	Continuous
Flash Point	30.0 °C	86.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Breakdown	>= 375 V	>= 375 V	

Processing Properties	Metric	English	Comments
Processing Temperature	10.0 - 32.2 °C	50.0 - 90.0 °F	Application Temperature
Dry Time	2 - 4 hour	2 - 4 hour	Recoat
Cure Time	30.0 - 60.0 min	0.500 - 1.00 hour	Air Set prior to curing
	30.0 - 60.0 min	0.500 - 1.00 hour	at 200°F; 0.75-1 hr at 480°F
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Color	Clear	
Dry Film Coverage ft2/gal	1208	at 1 mil
Thinner	MEK	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China