

Arkema Group EVATANE® 28-800 Copolymer Ethylene - Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

EVATANE® 28-800 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerisation process.

EVATANE® 28-800 is stabilized with antioxidants. The High Vinyl Acetate content of EVATANE® 28-800 brings softness, flexibility and polarity. EVATANE® 28-800 is compatible with tackifying resins and waxes. It's a useful product for hot melt adhesives formulation.

EVATANE® 28-800 delivers high cohesive strength with any kind of fillers (masterbatches). It can also be used as an additive for crude oil (pour point depressant) Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-EVATANE-28-800-Copolymer-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc @Temperature 23.0 °C	0.0343 lb/in ³ @Temperature 73.4 °F	ISO 1183
Vinyl Acetate Content	27 - 29 %	27 - 29 %	FTIR (internal)
Melt Index of Compound	700 - 900 g/10 min @Load 2.16 kg, Temperature 190 °C	700 - 900 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	ASTM D2240
Tensile Strength at Break	1.50 MPa	218 psi	ASTM D638
Elongation at Break	300 - 500 %	300 - 500 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	61.0 °C	142 °F	DSC
Vicat Softening Point	<= 40.0 °C @Load 0.999 kg	<= 104 °F @Load 2.20 lb	ISO 306
Ring & Ball Softening Point	76.0 °C	169 °F	ASTM E28

Processing Properties	Metric	English	Comments
Processing Temperature	<= 230 °C	<= 446 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China