

Arkema Group LOTADER® 3430 Terpolymer Ethylene - Acrylic Ester - Maleic Anhydride

Category : Polymer , Thermoplastic , EMAAA Terpolymer

Material Notes:

LOTADER 3430 is a random terpolymer of Ethylene, Acrylic Ester and Maleic Anhydride, polymerized by high-pressure autoclave process. LOTADER 3430 is a versatile adhesive for extrusion coating or lamination, designed as:Concentrate to be used in dry blend with LDPE. LOTADER 3430 improves adhesion of LDPE on alu foils, metallized or primerized films, oriented plastic films and particularly OPET. Ready for use resin to be used pure. LOTADER 3430 gives excellent adhesion on substrates like alu foil, metallized plastics, paper, board, PE and many plastic films.Coextrusion tie layer for PE/PA and PE/EVOH in extrusion coating process.Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-LOTADER-3430-Terpolymer-Ethylene-Acrylic-Ester-Maleic-Anhydride.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc @Temperature 23.0 °C	0.0340 lb/in ³ @Temperature 73.4 °F	ISO 1183
Methyl Acrylate Content	15 %	15 %	IRTF (internal)
Melt Index of Compound	6.0 g/10 min @Load 2.16 kg, Temperature 190 °C	6.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	30	30	ASTM D2240
Tensile Strength at Break	9.00 MPa	1310 psi	ASTM D638
Elongation at Break	750 %	750 %	ASTM D638
Flexural Modulus	0.0140 GPa	2.03 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	84.0 °C	183 °F	DSC
Vicat Softening Point	45.0 °C @Load 0.999 kg	113 °F @Load 2.20 lb	ASTM D1525
Brittleness Temperature	<= -50.0 °C	<= -58.0 °F	ASTM D726

Processing Properties	Metric	English	Comments
Processing Temperature	270 - 330 °C	518 - 626 °F	

Descriptive Properties	Value	Comments
Maleic Anhydride Content (%)	3.1	IRTF (internal)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China