

Arkema Group Orgalloy® LE 60LM Flexible Nylon Alloy (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon, Flexible Alloy

Material Notes:

LE series, flexible polyamide alloys: processability on PE screw, low moisture absorption, chemical resistance (no known solvents).ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Orgalloy-LE-60LM-Flexible-Nylon-Alloy-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Water Absorption	6.4 %	6.4 %	
Moisture Absorption at Equilibrium	1.8 %	1.8 %	Humidity Absorption
Melt Flow	1.2 g/10 min @Load 2.16 kg, Temperature 235 °C	1.2 g/10 min @Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.0 MPa	4640 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	6.0 %	6.0 %	50 mm/min
Tensile Modulus	0.700 GPa	102 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.10 mm	HB @Thickness 0.122 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China