

## Arkema Group Oroglas® V 920 T Acrylic, Injection Molding Grade (discontinued \*\*)

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

### Material Notes:

OROGLAS V 920 T is an injection molding grade with an improved thermal resistance HDT A ( 1.82 MPa ) = 96°C without any adverse effect on mechanical and optical properties. The processing of OROGLAS V 920 T remains easy due to its good flow behavior. MFI ( 230°C / 3.8kg ) = 6 gr / 10 min MVI ( 230°C / 3.8kg ) = 5.5 ml / 10 min OROGLAS V 920 T can be injection molded with any type of machine to produce any type of technical part. ISO data provided by the manufacturer, Arkema. Arkema, formed in 2004, was formerly Atofina Chemicals and before that Elf Atochem.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arkema-Group-Oroglas-V-920-T-Acrylic-Injection-Molding-Grade-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Arkema-Group-Oroglas-V-920-T-Acrylic-Injection-Molding-Grade-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	
Water Absorption	1.9 %	1.9 %	
Moisture Absorption at Equilibrium	0.30 %	0.30 %	Humidity Absorption
Melt Flow	5.5 g/10 min @Load 3.80 kg, Temperature 230 °C	5.5 g/10 min @Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	50 mm/min
Elongation at Break	6.0 %	6.0 %	Nominal Strain; 50 mm/min
Tensile Modulus	3.30 GPa	479 ksi	1 mm/min
Charpy Impact Unnotched	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	
Charpy Impact, Notched	0.200 J/cm <sup>2</sup>	0.952 ft-lb/in <sup>2</sup>	
Tensile Creep Modulus, 1 hour	2700 MPa	392000 psi	
Tensile Creep Modulus, 1000 hours	1800 MPa	261000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	65.0 µm/m-°C	36.1 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	101 °C	214 °F	50°C/hr; 50N
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Mfr. reports 'Transparent' but doesn't quantify.

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	3.2 @Frequency 1e+6 Hz	3.2 @Frequency 1e+6 Hz	
	3.7 @Frequency 100 Hz	3.7 @Frequency 100 Hz	
Dielectric Strength	19.7 kV/mm	500 kV/in	
Dissipation Factor	0.040 @Frequency 1e+6 Hz	0.040 @Frequency 1e+6 Hz	
	0.050 @Frequency 100 Hz	0.050 @Frequency 100 Hz	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China