

## Arkema Group Pebax® 3533 SA 01 MED Polyether Block Amide (PEBA)

Category : Polymer , Thermoplastic , Polyether Block Amide (PEBA)

### Material Notes:

Polyether block amide PEBAX® 3533 SA 01 MED is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices. PEBAX® 3533 SA 01 MED also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response. Upon request letters regarding USP Class IV testing can be provided. Information provided by Arkema Group

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arkema-Group-Pebax-3533-SA-01-MED-Polyether-Block-Amide-PEBA.php](http://www.lookpolymers.com/polymer_Arkema-Group-Pebax-3533-SA-01-MED-Polyether-Block-Amide-PEBA.php)

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.2 % @Temperature 23.0 °C, Time 86400 sec	1.2 % @Temperature 73.4 °F, Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	0.40 % @Temperature 20.0 °C	0.40 % @Temperature 68.0 °F	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 4.00 mm, Time 86400 sec	0.0050 in/in @Thickness 0.157 in, Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm @Thickness 4.00 mm, Time 86400 sec	0.0080 in/in @Thickness 0.157 in, Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	25	25	Conditioned 15 days at 23°C - 50% RH; ISO 868
	33	33	Instantaneous, Conditioned 15 days at 23°C - 50% RH; ISO 868
Tensile Strength at Break	39.0 MPa	5660 psi	Conditioned 15 days at 23°C - 50% RH; ASTM D638
Elongation at Break	>= 600 %	>= 600 %	Conditioned 15 days at 23°C - 50% RH; ASTM D638
Flexural Modulus	0.0210 GPa	3.05 ksi	Conditioned 15 days at 23°C - 50% RH; ISO 178
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179

Mechanical Properties	Metric	English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179
Charpy Impact, Notched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	144 °C	291 °F	ISO 11357
Vicat Softening Point	77.0 °C	171 °F	ISO 306
	@Load 1.02 kg	@Load 2.25 lb	

Processing Properties	Metric	English	Comments
Processing Temperature	205 °C	401 °F	Recommended Extrusion Temperature
	190 - 220 °C	374 - 428 °F	Extrusion Range
Nozzle Temperature	210 °C	410 °F	Recommended
	180 - 240 °C	356 - 464 °F	
Mold Temperature	10.0 - 30.0 °C	50.0 - 86.0 °F	
Drying Temperature	55.0 - 65.0 °C	131 - 149 °F	
Dry Time	4.00 - 8.00 hour	4.00 - 8.00 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China