

Arkema Group Rilsan® BMV Nylon 11 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 11 , Nylon 11 , Unreinforced

Material Notes:

Designation ISO 1874-PA11,M,18-010Rigid grade for injection molding. Available color: natural. Free additive.High impact strength. Easy filling of the mold due to its well adapted melt viscosity. Low shrinkage: include 1% on average for the design of the mold. Very good dimensional stability (low moisture absorption).Example applications: All sort of mechanical parts.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-BMV-Nylon-11-Dry.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	
Water Absorption	1.9 %	1.9 %	

Thermal Properties	Metric	English	Comments
Melting Point	183 °C	361 °F	10°C/min
Flammability, UL94	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-2	V-2	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China