

Arkema Group Rilsan® MA 4411 Nylon 12, Flexible Tubing Grade (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, Extrusion/Tubing Grade

Material Notes:

Designation ISO 1874-PA12-HI,EHL,22-003Flexible grade for tubes extrusion. Available colors: black and natural. Light and heat stabilized.Flexibility. High burst pressure and impact strength. Fit for use in a wide range of temperature. Very good chemical resistance.Example applications: Fuel line.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-MA-4411-Nylon-12-Flexible-Tubing-Grade-Conditioned.php

Physical Properties	Metric	English	Comments
Melt Flow	4.9 g/10 min	4.9 g/10 min	
	@Load 2.16 kg, Temperature 235 °C	@Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	22 %	22 %	50 mm/min
Tensile Modulus	0.500 GPa	72.5 ksi	1 mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	Low Temp
Charpy Impact, Notched	NB	NB	
	0.540 J/cm ² @Temperature -30.0 °C	2.57 ft-lb/in ² @Temperature -22.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China