

## Arlon 15370P020 0.020" (0.508 mm) Uncured Silicone Rubber on a Mylar Carrier

Category : Polymer , Thermoset , Silicone , Silicone Rubber

### Material Notes:

Design/Construction: Interleave: PolyethyleneSide 1: Uncured Silicone RubberCarrier: MylarAppearance: Pink high viscosity gumThis data represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-15370P020-0020-0508-mm-Uncured-Silicone-Rubber-on-a-Mylar-Carrier.php](http://www.lookpolymers.com/polymer_Arlon-15370P020-0020-0508-mm-Uncured-Silicone-Rubber-on-a-Mylar-Carrier.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	Arlon SQA-TMS-024
Thickness	38.1 microns	1.50 mil	Carrier
	76.2 microns	3.00 mil	Interleave
	508 microns	20.0 mil	Overall; Arlon SQA-TMS-003
	508 microns	20.0 mil	Side 1; Arlon SQA-TMS-003
Deformation	0.060 %	0.060 %	Silicone Property; Arlon SQA-TMS-005

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Blue	Interleave
	Pink	
Plasticity	6 mm	Arlon SQA-TMS-005
Total Product Weight (oz/yd <sup>2</sup> )	19	Arlon SQA-TMS-025

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China