

## Arlon 30580R030 0.030" (0.762 mm) Uncured Unsupported Silicone Rubber on Kodacel Carrier

Category : Polymer , Thermoset , Silicone , Silicone Rubber

### Material Notes:

Design/Construction:Side 1: Uncured Unsupported Silicone Rubber on Kodacel CarrierAppearance: Red silicone gum on polymer linerThis data represents typical values for the production material. The data should not be used to write, or in place of, material specificationsInformation provided by Arlon, Silicone Technologies Division

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-30580R030-0030-0762-mm-Uncured-Unsupported-Silicone-Rubber-on-Kodacel-Carrier.php](http://www.lookpolymers.com/polymer_Arlon-30580R030-0030-0762-mm-Uncured-Unsupported-Silicone-Rubber-on-Kodacel-Carrier.php)

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene Interleave
	127 microns	5.00 mil	Holland Cloth Carrier
	686 - 838 microns	27.0 - 33.0 mil	Overall
	686 - 838 microns	27.0 - 33.0 mil	Side 1

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	5.58 - 6.83 MPa	810 - 990 psi	Compound Property
Elongation at Break	540 - 660 %	540 - 660 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	rated per UL card E54153
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	

Processing Properties	15.0 min Metric	0.250 hour English	Comments Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month @Temperature 23.9 °C	6.00 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	28.4 - 34.4	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China